

TEST CERTIFICATE

No. F20207/6

Testing to EN ISO 12952 : 2010, Textiles – Assessment of the ignitability of Bedding Items

SAMPLE INFORMATION

Client **MIP(UK) Ltd**
2nd Floor, Clipper House, Leighton Industrial Park, Billington Road, Leighton Buzzard, Bedfordshire, LU7 4AJ.

Sample type **Fabric**

Details supplied by the client **FBSK5477**

Dimensions **200cm by 145cm (Full width)**

Date received **5/5/2020**

Pre-treatment **5 cycles according to BS EN ISO 6330, procedure 9N.**

Conditioning **To at least the minimum requirements of EN ISO 12952 : 2010, Clause 9**

TESTING

Following the pre-treatment above, the sample was conditioned and tested according to **EN ISO 12952 : 2010, Parts 1 & 2, Textiles - Assessment of the ignitability of Bedding Items** using Ignition Sources 0 and 1 applied to the sample laid flat over a mineral wool fibre pad.

The following results relate only to the ignitability of the test specimen under the particular conditions of test. They are not intended as a means of assessing the full potential fire hazard of the bedding items in use.

RESULTS

Specimen number	Time to extinction		Result	
	1	2	1	2
Smouldering Cigarette on top surface (min)	16	18	Non-ignition	Non-ignition
Smouldering Cigarette beneath top surface (min)	FTSL	FTSL	Non-ignition	Non-ignition
Small Open flame from above (sec)	0	0	Non-ignition	Non-ignition

CONCLUSION

The specimens tested showed Non-ignition when tested to EN ISO 12952 : 2010, Textiles - Assessment of the ignitability of Bedding Items, Part 1, and Non-ignition when tested to EN ISO 12952 : 2010, Textiles - Assessment of the ignitability of Bedding Items, Part 2.



Mr J Firth
Technical Manager
END OF REPORT